

Armourplan PVC Membrane Cleaner

Product Details

Material	Solvent Cleaner
Tin Size	5 Litre
Colour	Clear
Product Number	05501485



Introduction

- A solvent based solution
- Used to achieve satisfactory hot air weld between Armourplan membranes contaminated by moisture, building site dust and dirt
- Also used as a general cleaner to remove dirt or wet adhesive.

Features & Benefits

- Effective membrane weld preparation
- Cost effective application

PVC Membrane Cleaner Use

1. Wash / scrub the area of membrane where Armourplan PVC Cleaner is to be applied with warm soapy water
2. Allow to dry
3. Apply Armourplan PVC Cleaner to membrane using a clean lint free cloth wearing appropriate PPE in accordance with the MSDS
4. Allow Armourplan PVC Cleaner to fully evaporate prior to welding
5. If the membrane becomes wet or soiled after the preparation the cleaning regime is to be repeated
6. Ensure that the cap is firmly placed on the container when not in use.



Storage

Store in a sealed container in dry conditions at a temperature between 5°C and 25°C. Shelf life 12 months in an unopened container, stored at the above temperature

Typical Properties

Base	Hydrocarbon Solvent
Solid Content	N/A
Viscosity	Non - Viscous
Colour	Colourless
Tack Life	Approx. 5 minutes
Coverage Rate	20 m ² /litre
Flash Point	-35 Deg C (PMCC)
Shelf Life	12 months

Further Product Information

Full product literature, health & safety and technical sheets are available as downloads from our website www.ikopolymeric.com or on request by email polymeric.marketing@iko.com.



Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.

Company Registered in England No. 2678296 – Registered Office: Appley Lane North, Appley Bridge, Wigan, Lancashire, WN6 9AB

IKO Polymeric
Coney Green Road
Clay Cross, Chesterfield
S45 9HZ

T: 01257 488000
E: polymeric.technical.uk@iko.com
W: www.ikopolymeric.com