

Armourprep Heavy Duty PVC Membrane Cleaner

Product Details

Material	Acetone Cleaner
Tin Size	5 Litre
Colour	Clear
Product Number	46030001



Introduction

- An acetone based solution
- Used to achieve a satisfactory hot air weld between Armourplan membranes heavily contaminated by long term exposure to moisture, building site dust and dirt

Features & Benefits

- Effective membrane weld preparation
- Cost effective application

Armourprep Use

1. Wash / scrub the area of membrane where Armourprep solution is to be applied with warm soapy water
2. Allow to dry
3. Apply Armourprep to membrane using a clean lint free cloth wearing appropriate PPE in accordance with the MSDS
4. Allow Armourprep to fully evaporate prior to welding
5. If the membrane becomes wet or soiled after preparation the cleaning regime must be repeated
6. Avoid all contact between Armourprep and polystyrene insulation
7. Ensure that the cap is firmly placed on the container when not in use.

NOTE – Armourprep will only be supplied with prior agreement from the IKO Polymeric Technical Services Department



Storage

Store in a sealed container in dry conditions at a temperature between 5°C and 25°C. Shelf life 12 months in an unopened container, stored at the above temperature.

Typical Properties

Base	Acetone
Solid Content	0 %
Viscosity	N/A
Colour	Clear
Tack Life	N/A
Coverage Rate	20 m ² /litre
Flash Point	-17 °C
Shelf Life	12 months

Further Product Information

Full product literature, health & safety and technical sheets are available as downloads from our website www.ikopolymeric.com or on request by email polymeric.marketing@iko.com.



Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.

Company Registered in England No. 2678296 – Registered Office: Appley Lane North, Appley Bridge, Wigan, Lancashire, WN6 9AB

IKO Polymeric
 Coney Green Road
 Clay Cross, Chesterfield
 S45 9HZ

T: 01257 488000
E: polymeric.technical.uk@iko.com
W: www.ikopolymeric.com